

KYDEX® T

High impact fire-rated sheet

KYDEX® T is a proprietary thermoplastic sheet that is cost competitive with fire retardant ABS/PVC (FR-ABS) formulations but with significantly higher impact strength and extensibility.

Since KYDEX® T is less hygroscopic, unlike FR-ABS, it typically does not require pre-drying, offers superior impact, more uniform forming with less wall thinning and offers significantly greater resistance to a broad range of corrosive chemicals and cleaning solutions. It is available in a wide range of aesthetic choices and is Underwriter's Laboratories, Inc® recognized Std 94 V-0, 5V.

- Aircraft Interiors
- Equipment Housings
- Kiosk Housings
- Mass Transit Vehicle Interior Components
- Medical Products
- Substitute for FR-ABS sheet with competitive pricing but superior cost/performance
- Higher breakage resistance measured by the Notched Izod test than competitive thermoplastics
- Available in thicknesses from 0.71mm (0.028") and up, in eight textures, a variety of colors, custom blank sizes and low minimums
- Among the most rigid of thermoforming materials with a modulus of elasticity of 2,482 MPa (360,000 psi)
- Easy to form with excellent part definition and deep-draw characteristics
- Recognized by Underwriter's Laboratories, Inc® for Std 94 V-0, 5V in all thicknesses
- Form times similar to FR-ABS making it an easy transition from competitive products.

KYDEX, LLC is committed to ensuring that its products can be manufactured, transported, stored, used, disposed and recycled with an appropriate regard for safety, health and environmental protection. We support the safe handling of our products. Please contact our Technical Service department at 800.682.8758 for resources or visit our website: <http://www.kydex.com>. For Material Safety Data Sheets, please call 800.325.3133.

KYDEX, LLC

ISO 9001 and 14001 Certified

Customer Service

6685 Low St, Bloomsburg, PA 17815 USA
Phone: 800.325.3133, +1.570.389.5810
Outside the US: +1.570.389.5814
Fax: 800.452.0155, +1.570.387.7786
Email: info@kydex.com

Technical Service

Phone: 800.682.8758 ext. 581
Fax: +1.570.387.8722
Outside the US: +1.570.387.6997 ext. 581



KYDEX® T MC

Decorative aviation sheet which passes FAR paragraph (a)

Property	Test Method	Typical Value	
Specific Gravity	ASTM D-792	1.35	
Tensile Strength	ASTM D-638	42 MPa	6,100 psi
Elongation %	ASTM D-638	110	
Flexural Strength	ASTM D-790	66 MPa	9,600 psi
Modulus of Elasticity	ASTM D-790	2,480 MPa	360,000 psi
Notched Izod Impact Resistance, @ 23°C (73°F)	ASTM D-256	801 J/m	15 ft-lbs/in
Rockwell Hardness (R Scale)	ASTM D-785	94	
Heat Deflection Temperature (HDT) @ 264 psi (1.8 MPa) annealed	ASTM D-648	75.6°C	168°F
Flammability: Underwriters Laboratories, Inc® Component Recognition	UL Standard 94	V-0, 5V	
Federal Aviation Administration	FAR 25.853 (a)	Pass	
BS 476 Part 6		Class 0 (2.00mm)	
BS 476 Part 7		Class 1 (0.70 - 2.00mm)	
EC 95 / 28 / EG		Pass (1.00 - 6.00mm)	
DIN 5510-2		0.90mm (S4, ST2, SR2) 6.20mm (S4, ST2, SR1)	
M1 Test		M1 (0.70mm) M2 (3.20 - 6.40mm)	
Values based upon 3.18mm (0.125") sheet unless otherwise specified. Underwriters Laboratories, Inc®, File E115252 All thicknesses 0.71mm (0.028") and above * The thicknesses are added. Not intended for specification purposes.			

KYDEX, LLC

ISO 9001 and 14001 Certified

Customer Service

6685 Low St, Bloomsburg, PA 17815 USA

Phone: 800.325.3133, +1.570.389.5810

Outside the US: +1.570.389.5814

Fax: 800.452.0155, +1.570.387.7786

Email: info@kydex.com

Technical Service

Phone: 800.682.8758 ext. 581

Fax: +1.570.387.8722

Outside the US: +1.570.387.6997 ext. 581

Because we cannot anticipate or control the many different conditions under which this information and our products may be used, we do not guarantee the applicability of the accuracy of this information or the suitability of our products in any given situation. Users should conduct their own tests to determine the suitability of each product for their particular purposes. Data in the physical property table represents typical values and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions. Right to change physical properties as a result of technical progress is reserved. THE PRODUCTS DISCUSSED ARE SOLD WITHOUT WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE, EITHER EXPRESSED OR IMPLIED, EXCEPT AS PROVIDED IN OUR STANDARD TERMS AND CONDITIONS OF SALE. Buyer assumes all responsibility for loss or damage arising from the handling and use of our products, whether done in accordance with directions or not. In no event shall the supplier or the manufacturer be liable for incidental or consequential damages. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. Consult local code and regulatory agencies for specific requirements regarding code compliance, transporting, processing, recycling and disposal of our product. Product not intended for use as a heat resistant surface. Texture, product grade and other conditions may cause variations in appearance.

This information supersedes all previously published data.