

Stat-Rite® M809

PRODUCT DESCRIPTION

Stat-Rite® M809 is a static dissipative *Acrylic* alloy. Stat-Rite® M809 utilizes the patented Stat-Rite® inherently dissipative polymer (IDP) alloy system to provide clean, permanent ESD protection. Stat-Rite® IDP alloys provide consistent static dissipation even when extruded, injection molded or thermoformed into components.

Properties (typical)	M809	Units	Test Method
Host Polymer	Acrylic		
Filler	IDP Alloy		
Color	Translucent		
Specific Gravity	1.11	g/cc	ASTM D-792
Electrical properties:			
Surface Resistivity	1 x 10 ¹⁰	Ω/square	ASTM D-257 (50% R.H.)
Surface Resistance	9 x 10 ⁹	Ω	ESD S11.11 (12% R.H.)
Volume Resistivity	1 x 10 ¹⁰	Ω-cm	ASTM D-257
Static Decay Rate			
+5000 V to 50 V	.03	Seconds	FTMS-101C (12% R.H.)
-5000 V to -50 V	.04		
Mechanical properties:			
Tensile Strength @ Yield	3800 (27)	psi (MPa)	ASTM D-638
Tensile Elongation, Break	27	%	ASTM D-638
Tensile Modulus	219,000 (1510)	psi (MPa)	ASTM D-638
Flexural Modulus	210,000 (1450)	psi (MPa)	ASTM D-790-92
HDT @ 66 psi	167 (75)	° F (° C)	ASTM D-648
HDT @ 264 psi	153 (67)		ASTM D-648
Notched Izod Impact	2.6 (140)	ft-lb/in (J/m)	ASTM D-256-92
These are typical values and should not be used for establishing product specifications. Contact Noveon if you need data for this purpose.			

Stat-Rite® M809 is available in either sheet or pellet form.

Rev. April 24, 2002

FEATURES

- * Permanent static dissipative performance
- * Humidity insensitive
- * Contact clarity
- * Recyclable and reusable
- * Ultra-clean: low ionics

APPLICATIONS

- * Electronic assembly packaging
- * PCB tray packaging
- * Electronic component packaging

HANDLING CONSIDERATIONS

Properties of all Stat-Rite® polymer products in the molten state are adversely affected by moisture. Although Stat-Rite® products are dry when packaged, trace amounts of moisture can be absorbed during storage and handling. For best results, always keep product in unopened factory packaging until use.



The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained therefrom. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variations in methods, condi-

tions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Noveon shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond Noveon's direct

control. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.

Noveon, Inc. / 9911 Brecksville Road, Cleveland, Ohio 44141-3247

Phone: 888.234.2436 / Fax: 216.447.6232 / www.stat-rite.com



Stat-Rite[®] M809

PRODUCT DESCRIPTION

Stat-Rite[®] M809 is a static dissipative *Acrylic* alloy. Stat-Rite[®] M809 utilizes the patented Stat-Rite[®] inherently dissipative polymer (IDP) alloy system to provide clean, permanent ESD protection. Stat-Rite[®] IDP alloys provide consistent static dissipation even when extruded, injection molded or thermoformed into components.

TYPICAL CLEANROOM PROPERTIES:

Cleanroom Properties	Test Method	Test Results
Offgassing Components:	Noveon Test Method:	µg/g polymer
Total Organics	#3010-3	250
MMA		40
Styrene		15
Toluene		180
Ionic Content – Cations	Noveon Test Method:	ng/cm ²
Na		200
Ionic Content – Anions	Noveon Test Method:	ng/cm ²
Cl ⁻	#3010-4	20
NO ₃ ⁻		4
SO ₄ ⁻		15
PO ₄ ⁻		15

TYPICAL PERMANENCE PROPERTIES:

Permanence Test	Test Method	Surface Resistivity	Volume Resistivity
Original Sample at 50% RH	ASTM D-257	4E9	7E9
Original at 15% RH	ASTM D-257	2E10	5E10
Water Spray	MIL Spec 81705C	5E9	1E10
Solvent Wiped (IPA)	MIL Spec 81705C	6E9	9E9

noveon